

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 260 528 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
27.11.2002 Bulletin 2002/48

(51) Int Cl.⁷: **C08F 110/06**, C08F 297/08,
C08K 5/00, F16L 9/12

(21) Application number: **01112366.8**

(22) Date of filing: **21.05.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: **The designation of the inventor has not
yet been filed**

(74) Representative: **VA TECH Patente GmbH & Co
Stahlstrasse 21 a
4020 Linz (AT)**

(71) Applicant: **Borealis Technology OY
06201 Porvoo (FI)**

(54) **Propylene polymer pipes for pipelines**

(57) Single- or multilayer propylene polymer pipes and pipe components for pipelines with improved resistance to rapid crack propagation made from a propylene homopolymer with a melt index of 0.05 to 10 g/10 min at 230°C/2.16 kg or propylene block copolymer from 90.0 to 99.9 wt% of propylene and 0.1 to 10.0 wt% of α -olefins with 2 or 4 to 18 carbon atoms with a melt index of 0.05 to 8 g/10 min at 230°C/2.16 kg or mixtures thereof, wherein the propylene homopolymers or propylene block copolymers are β -nucleated propylene polymers, and the propylene polymer pipes for pipelines made from the β -nucleated propylene homopolymers have a

rapid crack propagation characterized by a critical temperature of -5 to + 40°C and a critical pressure ≥ 3 bar below the critical temperature and the propylene polymer pipes made from β -nucleated propylene block copolymers have a rapid crack propagation characterized by a critical temperature of -25 to 0°C and a critical pressure ≥ 3 bar below the critical temperature.

The propylene polymer pipes with improved resistance to rapid crack propagation are suitable for the transportation of fluids and pressurized fluids such as natural gas, water and the like.

EP 1 260 528 A1

Description

Background of the invention

[0001] The invention relates to propylene polymer single or multilayer pipes for pipelines with improved resistance to rapid crack propagation as well as to a process for producing them.

[0002] Olefin polymer pipes for pipelines consisting of ethylene polymers (Conference Papers "Plastic Pipeline Systems for the Millenium" Göteborg 1998, p. 841-842) or propylene block copolymers (Conference Papers "Plastic Pipeline Systems for the Millenium" Göteborg 1998, p. 611-620, 841-842) are known.

[0003] The disadvantage of pipelines made from conventional polypropylene pipes is the insufficient resistance against rapid crack propagation in pressure applications at and below room temperature or even below temperatures up to 40°C. Any small crack formed may propagate many kilometers causing complete destruction of the pipeline with obvious danger to the public. For a service temperature of for example 0°C, pipelines made of conventional polypropylene pipes have a critical pressure of approximately 1 bar, which is considerably below the normal service pressure.

Object of the invention

[0004] It is the object of the present invention to provide propylene polymer pipes for pipelines and pipeline components such as fittings, electrofusion fittings and valves including electrofusion valves with improved resistance to rapid crack propagation for pressure applications at temperatures below room temperature and particularly also below the freezing point.

Brief Description of the invention

[0005] According to the present invention, this object is achieved by propylene polymer pipes for pipelines with improved resistance to rapid crack propagation comprising a propylene homopolymer with a melt index of 0.05 to 8 g/10 min at 230°C/2.16 kg or propylene block copolymers from 90.0 to 99.9 wt% of propylene and 0.1 to 10.0 wt% of α -olefins with 2 or 4 to 18 carbon atoms with a melt index of 0.05 to 8 g/10 min at 230°C/2.16 kg or mixtures thereof, wherein the propylene homopolymers or propylene block copolymers are β -nucleated propylene polymers, and the propylene polymer pipes for pipelines made from the β -nucleated propylene homopolymers have a rapid crack propagation characterized by a critical temperature of -5 to + 40 °C and a critical pressure ≥ 3 bar below the critical temperature and the propylene polymer pipes made from β -nucleated propylene block copolymers have a rapid stress propagation characterized by a critical temperature of - 25 to 0 °C and a critical pressure ≥ 3 bar below the critical temperature.

Detailed description of the invention

[0006] β -nucleated propylene polymers are isotactic propylene polymers composed of chains in a 3_1 helical conformation having an internal microstructure of β -form spherulites being composed of radial arrays of parallel stacked lamellae. This microstructure can be realized by the addition of β -nucleating agents to the melt and crystallization. The presence of the β -form can be detected through the use of wide angle X-ray diffraction (Moore, J., Polypropylene Handbook, p. 134-135, Hanser Publishers Munich 1996).

[0007] Critical temperature and critical pressure are the important safety parameters for pressurized pipelines.

[0008] The critical temperature is the temperature, above which it is not possible to produce rapid crack propagation in pressurized pipelines. The critical temperature can be determined according to the S4 (Small Scale Steady State) Test described in ISO 13477, 1997.

[0009] The critical pressure is the pressure, under which it is not possible to produce rapid crack propagation (RCP) in pressurized pipelines. The critical pressure is determined at a temperature below the critical temperature as described in ISO 13477, 1997. In case the RCP test is difficult to perform (dimension of the pipe or design of pipe components) the test according to ISO 13477 should be performed with test pipes with a diameter of 110 mm and a wall thickness of 10 mm manufactured of the same material. Alternatively pipes can be manufactured by milling the pipe or pipe component and further extruding test pipes with diameter of 110 mm and a wall thickness of 10 mm as described and tested according to ISO 13477, 1997.

[0010] That is, the lower the critical temperature is, and the higher the critical pressure is, the safer the pipeline is.

[0011] The propylene homopolymers and the propylene copolymers according to the present invention have melt indices of 0.05 to 8 g/10 min at 230°C/2.16 kg, preferably 0.1 to 3 g/10 min at 230°C/2.16 kg, most preferably 0.2 to 3 g/10 min at 230°C/2.16 kg.

[0012] The single- or multilayer pipes produced by using the propylene homopolymers of the present inventions have

a critical temperature of -5 to +40°C, preferably -5 to +20°C, more preferably -5 to +10 °C, most preferably -5 to +5°C.

[0013] The single- or multilayer pipes produced by using the propylene copolymers of the present inventions have a critical temperature of -25 to 0°C, preferably -25 to -5°C, more preferably -25 to -10°C, most preferably -25 to -15°C.

[0014] The single- or multilayer pipes produced by using the propylene homo- and/or copolymers of the present inventions have a critical pressure of ≥3 bar, preferably ≥4 bar, most preferably ≥5bar below the critical temperature.

[0015] Preferably the critical pressure is determined 5°C below the critical temperature.

[0016] According to an advantageous embodiment of the present invention, the β-nucleated propylene polymers used for producing the single- or multilayer pipes and pipe components are β-nucleated propylene homopolymers having an IR_τ >0.98, a tensile modulus >1500 MPa and a Charpy impact strength, of ≥3 kJ/m² at -20°C using notched test specimens or the β-nucleated propylene block copolymers having an IR_τ of the propylene homopolymer block of >0.98, a tensile modulus ≥1100 MPa and a Charpy impact strength at -20°C of ≥6 kJ/m² using notched test specimens.


[0017] The IR_τ of the propylene polymers is measured by Infrared spectroscopy and calculated as described in EP 0 277 514 A2 on page 3.

[0018] According to the present invention the propylene homopolymers show a tensile modulus ≥1500 MPa, preferably ≥1600 MPa and the propylene copolymers show a tensile modulus ≥1100 MPa, preferably ≥1300 MPa and most preferably ≥1500 MPa.

[0019] The propylene homopolymers according to the present invention have a Charpy impact strength of ≥3 kJ/m² at -20°C, preferably 4 to 10 kJ/m² at -20°C, most preferably 5 to 10 kJ/m² at -20°C.

[0020] The propylene copolymers according to the present invention have a Charpy impact strength of ≥6 kJ/m² at -20°C, preferably ≥9kJ/m² at -20°C, most preferably ≥10 kJ/m² at -20°C. Charpy impact strength of up to at least 60 kJ/m² is possible for copolymers according to the invention.

[0021] According to an advantageous feature of the present invention, the β-nucleated propylene polymers used for the single- or multilayer pipes and pipe components with an IR_τ >0.98 are propylene polymers obtained by polymerization with a Ziegler-Natta catalyst system comprising titanium-containing solid components, an organoalumina, magnesium or titanium compound as cocatalyst and an external donor according to the formula



wherein R and R' are identical or different and are branched or cyclic aliphatic or aromatic hydrocarbon residues, and y and x independently from each other are 0 or 1, provided that x + y are 1 or 2.

[0022] Examples of propylene polymers with high stereospecificity (e.g. IR_τ values) obtained by polymerization with a Ziegler-Natta catalyst system are propylene polymers as described in EP-A-0 790 262, WO 99/24478 and WO 99/16797.

[0023] A preferred external donor of the Ziegler-Natta catalyst system for producing the propylene polymers suitable for the inventive propylene polymer to be used in the production of pipes and pipe components is dicyclopentylidimethoxysilane.

[0024] According to a preferred embodiment the β-nucleated propylene polymer of the inventive propylene polymer pipes contains 0.01 to 2.0 wt%, in each case based on the propylene polymers used, of

- dicarboxylic acid derivative type diamide compounds from C₅-C₈-cycloalkyl monoamines or C₆-C₁₂-aromatic monoamines and C₅-C₈-aliphatic, C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic dicarboxylic acids, preferably N,N'-di-C₅-C₈-cycloalkyl-2,6-naphthalene dicarboxamide compounds, N,N'-di-C₅-C₈-cycloalkyl-4,4-biphenyldicarboxamide compounds, N,N'-di-C₅-C₈-cycloalkylterephthalamide compounds, N,N'-di-C₅-C₈-cycloalkyl-1,4-cyclohexanedicarboxamide compounds and/or N,N'-di-C₆-C₁₂-aryl-C₅-C₈-diamide compounds; and/or
- diamine derivative type diamide compounds from C₅-C₈-cycloalkyl monocarboxylic acids or C₆-C₁₂-aromatic monocarboxylic acids and C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic diamines, preferably N,N'-C₆-C₁₂-arylene-bis-benzamide compounds, N,N'-C₅-C₈-cycloalkyl-bis-benzamide compounds, N,N'-p-C₆-C₁₂-arylene-bis-C₅-C₈-cycloalkylcarboxamide compounds and/or N,N'-C₅-C₈-cycloalkyl-bis-cyclohexanecarboxamide compounds; and/or
- amino acid derivative type diamide compounds from amidation reaction of C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-arylamino acids, C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic monocarboxylic acid chlorides and C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic mono-amines, preferably N-phenyl-5-(N-benzoylamino)pentaneamide and/or N-cyclohexyl-4-N-cyclohexylcarbonylamino benzamide,

as β-nucleating agent.

[0025] Examples of N,N'-di-C₅-C₈-cycloalkyl -2,6-naphthalene dicarboxamide compounds are

N,N'-dicyclohexyl-2,6-naphthalene dicarboxamide and

N,N'-dicyclooctyl-2,6-naphthalene dicarboxamide.

[0026] Examples of N,N'-di-C₅-C₈-cycloalkyl-4,4-biphenyldicarboxamide compounds are

N,N'-dicyclohexyl-4,4-biphenyldicarboxamide and
N,N'-dicyclopentyl-4,4-biphenyldicarboxamide.

[0027] Examples of N,N'-di-C₅-C₈-cycloalkyl-terephthalamide compounds are

N,N'-dicyclohexylterephthalamide and
N,N'-dicyclopentylterephthalamide.

[0028] Examples of N,N'-di-C₅-C₈-cycloalkyl-1,4-cyclohexanedicarboxamide compounds are

N,N'-dicyclohexyl-1,4-cyclohexanedicarboxamide and
N,N'-dicyclohexyl-1,4-cyclopentanedicarboxamide.

[0029] Examples of N,N'-di-C₆-C₁₂-aryl-C₅-C₈-diamide compounds are

N,N'-bis(p-methylphenyl)hexanediamide,
N,N'-bis(4-cyclohexylphenyl)hexanediamide,
N,N'-diphenylhexanediamide,
N,N'-diphenyloctanediamide and
N,N'-bis(p-ethylphenyl)hexanediamide.

[0030] Examples of N,N'-C₆-C₁₂-arylene-bis-benzamide compounds are

N,N'-p-phenylene-bis-benzamide and
N,N'-1,5-naphthalene-bis-benzamide.

[0031] Examples of N,N'-C₅-C₈-cycloalkyl-bis-benzamide compounds are

N,N'-1,4-cyclopentane-bis-benzamide and
N,N'-1,4-cyclohexane-bis-benzamide.

[0032] Examples of N,N'-p-C₆-C₁₂-arylene-bis-C₅-C₈-cycloalkylcarboxamide compounds are

N,N'-1,5-naphthalene-bis-cyclohexanecarboxamide and
N,N'-1,4-phenylene-bis-cyclohexanecarboxamide.

[0033] Examples of N,N'-C₅-C₈-cycloalkyl-bis-cyclohexanecarboxamide compounds are


N,N'-1,4-cyclopentane-bis-cyclohexanecarboxamide and
N,N'-1,4-cyclohexane-bis-cyclohexanecarboxamide.

[0034] According to a further preferred embodiment the β -nucleated propylene polymer of the inventive propylene polymer pipes contains 0.0001 to 2.0 wt%, in each case based on the propylene polymers used, of quinacridone type compounds, preferably quinacridone; dimethylquinacridone and/or dimethoxyquinacridone; quinacridonequinone type compounds, preferably quinacridonequinone, a mixed crystal of 5,12-dihydro(2,3b)acridine-7,14-dione with quino (2,3b)acridine-6,7,13,14-(5H,12H)-tetrone as disclosed in EP-B 0 177 961 and/or dimethoxyquinacridonequinone; and/or dihydroquinacridone type compounds, preferably dihydroquinacridone, dimethoxydihydroquinacridone and/or dibenzodihydroquinacridone, as β -nucleating agent.

[0035] According to a further preferred embodiment the β -nucleated propylene polymer of the inventive propylene polymer pipes contains 0.01 to 2.0 wt%, in each case based on the propylene polymers used, dicarboxylic acid salts of metals from group IIa of periodic system, preferably pimelic acid calcium salt and/or suberic acid calcium salt; and/or mixtures of dicarboxylic acids and salts of metals from group IIa of periodic system, as β -nucleating agent.

According to a further preferred embodiment the β -nucleated propylene polymer of the inventive propylene polymer pipes contains 0.01 to 2.0% by weight, in each case based on the propylene polymers used, salts of metals from group

Ila of periodic system and imido acids of the formula



wherein $x = 1$ to 4 ; $\text{R} = \text{H}$, $-\text{COOH}$, $\text{C}_1\text{-C}_{12}\text{-alkyl}$, $\text{C}_5\text{-C}_8\text{-cycloalkyl}$ or $\text{C}_6\text{-C}_{12}\text{-aryl}$, and $\text{Y} = \text{C}_1\text{-C}_{12}\text{-alkyl}$, $\text{C}_5\text{-C}_8\text{-cycloalkyl}$ or $\text{C}_6\text{-C}_{12}\text{-aryl}$ - substituted bivalent $\text{C}_6\text{-C}_{12}\text{-aromatic}$ residues, preferably calcium salts of phthaloylglycine, hexahydrophthaloylglycine, N-phthaloylalanine and/ or N-4-methylphthaloylglycine, as β -nucleating agent.

[0036] The inventive propylene polymers used for producing pipes for pipelines may further contain usual auxiliary materials for example 0.01 to 2.5 wt% stabilizers and/or 0.01 to 1 wt% processing aids and/or 0.1 to 1 wt% antistatic agents and/or 0.2 to 3 wt% pigments, in each case based on the propylene polymers used.

[0037] As stabilizers preferably mixtures of 0.01 to 0.6 wt% phenolic antioxidants, 0.01 to 0.6 wt% 3-arylbenzofuranones, 0.01 to 0.6 wt% processing stabilizers based on phosphites, 0.01 to 0.6 wt% high temperature stabilizers based on disulfides and thioethers and/or 0.01 to 0.8 wt% sterically hindered amines (HALS) are suitable.

[0038] A still further object of the present invention is a process for producing propylene polymer pipes and pipe components for pipelines with improved resistance to rapid crack propagation from a propylene homopolymer with a melt index of 0.05 to 8 g/10 min at $230^\circ\text{C}/2.16$ kg or propylene block copolymers from 90.0 to 99.9 wt% of propylene and 0.1 to 10.0 wt% of α -olefins with 2 or 4 to 18 carbon atoms with a melt index of 0.05 to 8 g/10 min at $230^\circ\text{C}/2.16$ kg or mixtures thereof, wherein the propylene homopolymers or propylene block copolymers are β -nucleated propylene polymers, and the propylene polymer pipes for pipelines made from the β -nucleated propylene homopolymers have a rapid crack propagation characterized by a critical temperature of -5 to $+40^\circ\text{C}$ and a critical pressure ≥ 3 bar below the critical temperature and the propylene polymer pipes and pipe components made from β -nucleated propylene block copolymers have a rapid crack propagation characterized by a critical temperature of -25 to 0°C and a critical pressure ≥ 3 bar below the critical temperature.

[0039] For producing the inventive single- or multilayer propylene polymer pipes and pipe components for pipelines conventional extruders or injection molding machines are suitable. For example, extruders with short compression screws or 3-zone screws with L/D 20 to 40 are suitable for melting the propylene polymer pursuant to the inventive method. Preferably, 5-zone screws with a feed zone, compression zone, shear zone, decompression zone and homogenizing zone are preferred. Screws with cutting depths of $1 : 2.5$ to $1 : 3.5$ are particularly suitable. Extruders equipped with a grooved barrel section are also suitable. Optionally, a melt pump and/or a static mixer can be used additionally between the extruder and the ring die head. Ring shaped dies with diameters ranging from approximately 16 to 2000 mm and greater are possible. Advantageous die temperatures for discharging the melt are 190 to 240°C . After leaving the ring-shaped die, the polyolefin pipes are taken off over a vacuum calibrating sleeve, and cooled.

[0040] Pipes could be manufactured by other extrusion processes such as injection molding, extrusion winding, rotor molding and blow molding and other appropriate processes.

[0041] Preferred applications of the propylene polymer pipes for pipelines are the conveyance of fluids and pressurized fluids such as natural gas and water and the like at service temperatures below room temperature and particularly also below the freezing point when applicable.

Examples

[0042] The following tests were made using injection molded test specimens prepared according to ISO 1873. Tensile modulus according to ISO 527 (cross head speed 1 mm/min) at $+23^\circ\text{C}$ Charpy impact strength, notched, according to ISO 179/1eA at -20°C Rapid crack propagation test on extruded pipes according to ISO 13477

Example 1

1.1 Preparation of the β -nucleated propylene polymer

[0043] A mixture of 90% by weight of a propylene block copolymer, obtained by combined bulk and gas phase polymerization using a Ziegler-Natta catalyst system with dicyclopentylmethoxysilane as external donor, having an ethylene content of 8.3 wt%, an IRt of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at $230^\circ\text{C}/2.16$ kg,

10% by weight of a master batch comprising 99 parts by weight of a propylene block copolymer having an ethylene content of 8.3% by weight, an $IR\tau$ of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 1 part by weight of pimelic acid calcium salt, and 0.1 wt% calcium stearate, 0.1 wt% tetrakis [methylene(3,5-di-t-butylhydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butylphenyl)phosphite, based on

the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/185/210/220/225/225/220/200/185°C, homogenized, discharged and pelletized.

The resulting polypropylene polymer has a melt index of 0.32 g/10 min at 230°C/2.16 kg, a tensile modulus of 1290 MPa and a Charpy impact strength, using notched test specimens, of 39 kJ/m² at -20 °C.

1.2 Manufacture of the propylene polymer pipe for pipelines

[0044] For producing the propylene polymer pipes for pipelines, the β -nucleated propylene polymer of 1.1 is introduced in a single screw extruder (L/D=30, D=70mm, temperature profile 200/210/220/220/220/220/200°C, 40 rpm), melted, extruded through a ring shaped die with a diameter of 110 mm, taken off over a vacuum calibrating sleeve as a pipe of a diameter of 110 mm and a wall thickness of 10 mm, and cooled in a 6 m water bath at 20°C, the taking off velocity being 0.3 m/min.

Rapid crack propagation test shows a critical temperature of -21 °C and a critical pressure of 8 bar at -26°C.

Example 2

2.1 Preparation of the β -nucleated propylene polymer

[0045] A mixture of

94% by weight of a propylene homopolymer, obtained by bulk polymerization using a Ziegler-Natta catalyst system with dicyclopentyldimethoxysilane as external donor, having an $IR\tau$ of 0.985, and a melt index of 1.1 g/10 min at 230°C/2.16 kg,

6% by weight of a master batch comprising 99.8 parts by weight of a propylene block copolymer having an ethylene content of 8.3 wt%, an $IR\tau$ of the propylene homopolymer block of 0.985 and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 0.2 parts by weight of a mixed crystal of 5,12-dihydro(2,3b)acridine-7,14-dione with quino(2,3b)acridine-6,7,13,14-(5H,12H)-tetrone, and 0.05 wt% calcium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butyl-hydroxyhydrocinnamate)]methane and 0.1 wt% tris-(2,4-di-t-butyl-phenyl)-phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/190/215/225/230/230/215/205/190°C, homogenized, discharged and pelletized.

[0046] The resulting polypropylene polymer has a melt index of 1.0 g/10 min at 230°C/2.16 kg, a tensile modulus of 1500 MPa and a Charpy impact strength, using notched test specimens, of 11 kJ/m² at -20 °C.

2.2. Manufacture of the propylene polymer pipe for pipelines

[0047] For producing the propylene polymer pipes for pipelines, the β -nucleated propylene polymer of 2.1 is introduced in a single screw extruder (L/D=30, D=70mm, temperature profile 200/210/225/225/225/205°C, 40 rpm), melted, extruded through a ring shaped die with a diameter of 110 mm, taken off over a vacuum calibrating sleeve as a pipe of a diameter of 110 mm and a wall thickness of 10 mm, and cooled in a 6 m water bath at 20°C, the taking off velocity being 0.35 m/min.

[0048] Rapid Crack Propagation test results a critical temperature of -5°C and a critical pressure of 5 bar at -10°C.

Example 3

3.1 Preparation of the β -nucleated propylene polymer

[0049] A mixture of

75% by weight of a propylene block copolymer obtained by combined bulk and gas phase polymerization using a Ziegler-Natta catalyst system with dicyclopentyldimethoxysilane as external donor, having an ethylene content of 8.3 wt%, an $IR\tau$ of the propylene homopolymer block of 0.985 and a melt index of 0.30 g/10 min at 230°C/2.16 kg,

25% by weight of a master batch comprising 99.5 parts by weight of a propylene block copolymer having an ethylene content of 8.3 wt%, an $IR\tau$ of the propylene homopolymer block of 0.985, and a melt index of 0.30 g/10 min at 230°C/2.16 kg, and 0.5 parts by weight of hexahydrophthaloylglycine calcium salt, and 0.1 wt% calcium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butylhydroxyhydrocinnamate)]methane and 0.1 wt% of tris-(2,4-di-t-butylphenyl)phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of

100/145/185/210/220/225/225/200/185°C, homogenized, discharged and pelletized.

The resulting polypropylene polymer has a melt index of 0.32 g/10 min at 230°C/2.16 kg, a tensile modulus of 1310 MPa and a Charpy impact strength, notched, of 37 kJ/m² at -20°C.

3.2 Manufacture of the propylene polymer pipe for pipelines

[0050] For producing the propylene polymer pipes for pipelines, the β -nucleated propylene polymer of 3.1 is introduced in a single screw extruder (L/D=30, D=70mm, temperature profile 200/210/220/220/220/220/200°C, 40 rpm), melted, extruded through a ring shaped die with a diameter of 110 mm, taken off over a vacuum calibrating sleeve as a pipe of a diameter of 110 mm and a wall thickness of 10 mm, and cooled in a 6 m water bath at 20°C, the taking off velocity being 0.3 m/min.

Rapid Crack Propagation test results a critical temperature of -19°C and a critical pressure of 7 bar at -24°C.

Example 4

4.1 Preparation of the β -nucleated propylene polymer

[0051] A mixture of

95 wt% of a propylene homopolymer, obtained by gas phase polymerization using a Ziegler-Natta catalyst system with dicyclopentylidimethoxysilane as external donor, having an IR_T of 0.987, and a melt index of 1.1 g/10 min at 230°C/2.16 kg,

5 wt% of a master batch comprising 97.5 parts by weight of a propylene homopolymer having an IR_T of 0.987, and a melt index of 4.2 g/10 min at 230°C/2.16 kg, and 2.5 parts by weight of N,N'-dicyclohexyl-2,6-naphthalene dicarboxamide, and 0.05 wt% calcium stearate, 0.1 wt% tetrakis[methylene(3,5-di-t-butylhydroxyhydrocinnamate)]-methane and 0.1 wt% tris-(2,4-di-t-butylphenyl)phosphite, based on the sum of the propylene polymers used, is melted in a twin screw extruder with a temperature profile of 100/145/190/215/225/225/225/205/190°C, homogenized, discharged and pelletized.

[0052] The resulting polypropylene polymer has a melt index of 1.2 g/10 min at 230°C/2.16 kg, a tensile modulus of 1765 MPa and a Charpy impact strength, using notched test specimens, of 5.5 kJ/m² at -20°C.

4.2 Manufacture of the propylene polymer pipe for pipelines


[0053] For producing the propylene polymer pipes for pipelines, the β -nucleated propylene polymer of 4.1 is introduced in a single screw extruder (UD=30, D=70mm, temperature profile 200/210/225/225/225/225/205°C, 40 rpm), melted, extruded through a ring shaped die with a diameter of 110 mm, taken off over a vacuum calibrating sleeve as a pipe of a diameter of 110 mm and a wall thickness of 10 mm, and cooled in a 6 m water bath at 20°C, the taking off velocity being 0.35 m/min.

[0054] Rapid Crack Propagation test results a critical temperature of +2.5°C and a critical pressure of 5 bar at -2.5°C.

Claims

1. Propylene polymer single- or multilayer pipes and pipe components for pipelines with improved resistance to rapid crack propagation comprising a propylene homopolymer with a melt index of 0.05 to 8 g/10 min at 230°C/2.16 kg or propylene block copolymers from 90.0 to 99.9 wt% of propylene and 0.1 to 10.0 wt% of α -olefins with 2 or 4 to 18 carbon atoms with a melt index of 0.05 to 8 g/10 min at 230°C/2.16 kg or mixtures thereof, wherein the propylene homopolymers or propylene block copolymers are β -nucleated propylene polymers, and the propylene polymer pipes for pipelines made from the β -nucleated propylene homopolymers have a rapid crack propagation **characterized by** a critical temperature of -5 to +40°C and a critical pressure ≥ 3 bar below the critical temperature and the propylene polymer pipes made from β -nucleated propylene block copolymers have a rapid crack propagation **characterized by** a critical temperature of -25 to 0°C and a critical pressure ≥ 3 bar below the critical temperature.
2. Propylene polymer pipes and pipe components according to claim 1, wherein the β -nucleated propylene polymers of the propylene polymer pipes are β -nucleated propylene homopolymers having an IR_T >0.98, a tensile modulus >1500 MPa at +23°C and a Charpy impact strength, of ≥ 3 kJ/m² at -20°C using notched test specimens or the β -nucleated propylene block copolymers having an IR_T of the propylene homopolymer block of 0.98, a tensile modulus ≥ 1100 MPa at 23°C and a Charpy impact strength at -20°C of ≥ 6 kJ/m² using notched test specimens.

3. Propylene polymer pipes according to claim 2, wherein the β -nucleated propylene polymers with an $IR_{\tau} > 0.98$ being propylene polymers obtained by polymerization with a Ziegler-Natta catalyst system comprising titanium-containing solid components, an organoalumina, magnesium or titanium compound as cocatalyst and an external donor according to the formula




wherein R and R' are identical or different and are branched or cyclic aliphatic or aromatic hydrocarbon residues, and y and x independently from each other are 0 or 1, provided that x + y are 1 or 2.

4. Propylene polymer pipes according to claim 3, wherein the external donor is dicyclopentyl dimethoxysilane.
5. Propylene polymer pipes of one of claims 1 to 4, wherein the β -nucleated propylene polymer contains 0.01 to 2.0 wt%, in each case based on the propylene polymers used, of

- dicarboxylic acid derivative type diamide compounds from C₅-C₈-cycloalkyl monoamines or C₆-C₁₂-aromatic monoamines and C₅-C₈-aliphatic, C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic dicarboxylic acids, preferably N, N'-di-C₅-C₈-cycloalkyl-2,6-naphthalene dicarboxamide compounds, N, N'-di-C₅-C₈-cycloalkyl-4,4-biphenyldicarboxamide compounds, N, N'-di-C₅-C₈-cycloalkylterephthalamide compounds, N, N'-di-C₅-C₈-cycloalkyl-1,4-cyclohexanedicarboxamide compounds and/or N, N'-di-C₆-C₁₂-aryl-C₅-C₈-diamide compounds; and/or
- diamine derivative type diamide compounds from C₅-C₈-cycloalkyl monocarboxylic acids or C₆-C₁₂-aromatic monocarboxylic acids and C₅-C₈-cycloaliphatic or C₆-C₁₂-aromatic diamines, preferably N, N' - C₆-C₁₂-arylene-bis-benzamide compounds, N, N'-C₅-C₈-cycloalkyl-bis-benzamide compounds, N, N'-p-C₆-C₁₂-arylene-bis-C₅-C₈-cycloalkylcarboxamide compounds and/or N, N'-C₅-C₈-cycloalkyl-bis-cyclohexanecarboxamide compounds; and/or
- amino acid derivative type diamide compounds from amidation reaction of C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-arylamino acids, C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic monocarboxylic acid chlorides and C₅-C₈-alkyl-, C₅-C₈-cycloalkyl- or C₆-C₁₂-aromatic monoamines, preferably N-phenyl-5-(N-benzoylamino) pentaneamide and/or N-cyclohexyl-4-N-cyclohexylcarbonylamino benzamide,

as β -nucleating agent.

6. Propylene polymer pipes of one of claims 1 to 4, wherein the β -nucleated propylene polymer contains 0.0001 to 2.0 wt%, based on the polypropylene used, quinacridone type compounds, preferably quinacridone, dimethylquinacridone and/or dimethoxyquinacridone; quinacridonequinone type compounds, preferably quinacridonequinone, a mixed crystal of 5,12-dihydro(2,3b)acridine-7,14-dione with quino(2,3b)acridine-6,7,13,14-(5H,12H)-tetrone and/or dimethoxyquinacridonequinone; and/or dihydroquinacridone type compounds, preferably dihydroquinacridone, dimethoxydihydroquinacridone and/or dibenzodihydroquinacridone, as β -nucleating agent.
7. Propylene polymer pipes of one of claims 1 to 4, wherein the β -nucleated propylene polymer contains 0.01 to 2.0 wt%, based on the polypropylene used, dicarboxylic acid salts of metals from group IIa of periodic system, preferably pimelic acid calcium salt and/or suberic acid calcium salt; and/or mixtures of dicarboxylic acids and salt of metals from group IIa of periodic system, as β -nucleating agent.
8. Propylene polymer pipes of one of claims 1 to 4, wherein the β -nucleated propylene polymer contains 0.01 to 2.0 wt%, based on the polypropylene used, salts of metals from group IIa of periodic system and imido acids of the formula



wherein x = 1 to 4; R = H, -COOH, C₁-C₁₂-alkyl, C₅-C₈-cycloalkyl or C₆-C₁₂-aryl, and Y = C₁-C₁₂-alkyl, C₅-C₈-

cycloalkyl or C₆-C₁₂-aryl - substituted bivalent C₆-C₁₂-aromatic residues, preferably calcium salts of phthaloylglycine, hexahydrophthaloylglycine, N-phthaloylalanine and/ or N-4-methylphthaloylglycine, as β -nucleating agent.

9. A process for producing single- or multilayer propylene polymer pipes and pipe components for pipelines with improved resistance to rapid crack propagation from a propylene homopolymer with a melt index of 0.05 to 8 g/10 min at 230°C/2.16 kg or propylene block copolymers from 90.0 to 99.9 wt% of propylene and 0.1 to 10.0 wt% of α -olefins with 2 or 4 to 18 carbon atoms with a melt index of 0.05 to 8 g/10 min at 230 °C/2.16 kg or mixtures thereof, wherein the propylene homopolymers or propylene block copolymers are β -nucleated propylene polymers, and the propylene polymer pipes for pipelines made from the β -nucleated propylene homopolymers have rapid crack propagation properties **characterized by** a critical temperature of -5 to + 40°C and a critical pressure ≥ 3 bar below the critical temperature and the propylene polymer pipes made from β -nucleated propylene block copolymers have a rapid crack propagation **characterized by** a critical temperature of -25 to 0°C and a critical pressure ≥ 3 bar below the critical temperature.
10. Use of propylene polymer pipes for pipelines of one of claims 1 to 8 for the conveyance of fluids and pressurized fluids such as natural gas and water and the like.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 11 2366

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	WO 99 24479 A (BOREALIS AS ;JAEAESKELAEINEN PIRJO (FI); MALM BO (FI); HUOVINEN PA) 20 May 1999 (1999-05-20)	1-4,9,10	C08F110/06 C08F297/08 C08K5/00 F16L9/12
Y	* claims; examples; tables *	1-10	
X	WO 97 13790 A (BOREALIS AS ;ANDTSJOE HENRIK (FI); PENTTI ISMO (FI); HARLIN ALI (F) 17 April 1997 (1997-04-17)	1-3,9,10	
	* page 11, line 16 - line 20; claims; examples 6,8 *		
X	EP 0 714 923 A (SHOWA DENKO KK) 5 June 1996 (1996-06-05)	1-4,9,10	
	* page 7, line 48 - page 8, line 5; claims; examples; tables *		
X	WO 99 40151 A (BERNREITNER KLAUS ;KONRAD ROLAND (AT); EBNER KARL (AT); PCD POLYME) 12 August 1999 (1999-08-12)	1,2,5,9,10	
	* the whole document *		
X	DE 297 22 949 U (DANUBIA PETROCHEM POLYMERE) 26 February 1998 (1998-02-26)	1,2,9,10	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C08F C08L C08K
	* page 6, line 30; claims; examples *		
D,Y	EP 0 177 961 A (DANUBIA PETROCHEMIE) 16 April 1986 (1986-04-16)	1-10	
	* claims; examples; table 3 *		
D,Y	EP 0 790 262 A (CHISSO CORP) 20 August 1997 (1997-08-20)	1-10	
	* page 8, line 50 - page 18, line 56; claims *		
E	WO 01 40327 A (BASELL POLYOLEFINE GMBH ;BOEHM THOMAS (DE); DOLLE VOLKER (DE); FRA) 7 June 2001 (2001-06-07)	1,2,9,10	
	* claims; examples *		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 23 October 2001	Examiner Kaumann, E
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons</p> <p>&: member of the same patent family, corresponding document</p>			

EPC FORM 1503 03 82 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 2366

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

23-10-2001

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
WO 9924479	A	20-05-1999	AU	1035799 A	31-05-1999
			BR	9814854 A	03-10-2000
			CN	1285851 T	28-02-2001
			EP	1028985 A1	23-08-2000
			WO	9924479 A1	20-05-1999
WO 9713790	A	17-04-1997	FI	954814 A	11-04-1997
			AT	188711 T	15-01-2000
			AU	704614 B2	29-04-1999
			AU	7218296 A	30-04-1997
			BR	9610966 A	02-03-1999
			CN	1202177 A	16-12-1998
			DE	69606188 D1	17-02-2000
			DE	69606188 T2	08-06-2000
			EP	0854887 A1	29-07-1998
			ES	2142615 T3	16-04-2000
			WO	9713790 A1	17-04-1997
			US	6084041 A	04-07-2000
			ZA	9608558 A	20-05-1997
EP 0714923	A	05-06-1996	AU	705455 B2	20-05-1999
			AU	3790395 A	30-05-1996
			CA	2162946 A1	22-05-1996
			CN	1128767 A	14-08-1996
			DE	69517771 D1	10-08-2000
			DE	69517771 T2	23-11-2000
			EP	0714923 A1	05-06-1996
			JP	3002119 B2	24-01-2000
			JP	8198922 A	06-08-1996
			US	5703172 A	30-12-1997
			US	5804665 A	08-09-1998
			JP	3034452 B2	17-04-2000
			JP	8198923 A	06-08-1996
WO 9940151	A	12-08-1999	WO	9940151 A1	12-08-1999
			EP	1044240 A1	18-10-2000
			NO	20003821 A	26-07-2000
DE 29722949	U	26-02-1998	DE	29722949 U1	26-02-1998
EP 0177961	A	16-04-1986	AT	381110 A	25-08-1986
			AT	322984 A	15-01-1986
			CS	8507292 A3	18-11-1992
			DE	3443599 A1	17-04-1986
			DE	3561399 D1	18-02-1988
			EP	0177961 A2	16-04-1986

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 2366

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

23-10-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0177961 A		HU 40152 A2	28-11-1986
		SK 277920 B6	09-08-1995
EP 0790262 A	20-08-1997	AU 717990 B2	06-04-2000
		AU 6838296 A	19-03-1997
		DE 69608240 D1	15-06-2000
		DE 69608240 T2	23-11-2000
		EP 0790262 A1	20-08-1997
		US 6005034 A	21-12-1999
		CA 2203876 A1	06-03-1997
		WO 9708218 A1	06-03-1997
		TW 416962 B	01-01-2001
WO 0140327 A	07-06-2001	DE 19957384 A1	31-05-2001
		AU 1280301 A	12-06-2001
		WO 0140327 A1	07-06-2001

EPO FORM P0489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

PUB-NO: EP001260528A1
DOCUMENT-IDENTIFIER: EP 1260528 A1
TITLE: Propylene polymer pipes for pipelines
PUBN-DATE: November 27, 2002

ASSIGNEE-INFORMATION:

NAME	COUNTRY
BOREALIS TECH OY	FI

APPL-NO: EP01112366
APPL-DATE: May 21, 2001

PRIORITY-DATA: EP01112366A (May 21, 2001)

INT-CL (IPC): C08F110/06 , C08F297/08 ,
C08K005/00 , F16L009/12

EUR-CL (EPC): C08F010/06 , C08F110/06 ,
C08F297/08 , C08K005/00 ,
C08K005/00 , F16L009/12

ABSTRACT:

CHG DATE=20030114 STATUS=O> Single- or multilayer propylene polymer pipes and pipe components for pipelines with improved resistance to rapid crack propagation made from a propylene homopolymer with a melt index of 0.05 to 10 g/10 min at 230 DEG C/2.16 kg or propylene block copolymer from 90.0 to 99.9 wt% of propylene and

0.1 to 10.0 wt% of alpha -olefins with 2 or 4 to 18 carbon atoms with a melt index of 0.05 to 8 g/10 min at 230 DEG C/2.16 kg or mixtures thereof, wherein the propylene homopolymers or propylene block copolymers are beta -nucleated propylene polymers, and the propylene polymer pipes for pipelines made from the beta -nucleated propylene homopolymers have a rapid crack propagation characterized by a critical temperature of -5 to + 40 DEG C and a critical pressure ≥ 3 bar below the critical temperature and the propylene polymer pipes made from beta -nucleated propylene block copolymers have a rapid crack propagation characterized by a critical temperature of -25 to 0 DEG C and a critical pressure ≥ 3 bar below the critical temperature. The propylene polymer pipes with improved resistance to rapid crack propagation are suitable for the transportation of fluids and pressurized fluids such as natural gas, water and the like.